
FELOSAN RME

Characterization	Low foaming wetting and washing agent for application in pretreatment
Chemical Structure	Fatty alcohol ethoxylate
Supplied Form	Colourless, clear liquid
Ionic Character	Non-ionic
pH-Value	6.0 – 8.0
Specific weight at 20°C	Approx. 1.0
Stability	<p>FELOSAN RME is very stable to the usual concentrations of acids, alkalis, and hardening agents of water.</p> <p>FELOSAN RME is sensitive to frost. The frozen product should be melted and mixed thoroughly and homogenized.</p>
Storage	In a cool and dry place in well closed, original containers. We recommend not to exceed a storage time of 12 months.

Properties

FELOSAN RME has an excellent wetting capacity and good washing properties. The product has very good emulsifying capacity for oil and thus is suitable for the elimination of oil and fat soilings.

FELOSAN RME can be used in all pretreatment processes.

Application technique

Diluting Instructions

FELOSAN RME can be diluted with cold water at every ratio.

Application fields

FELOSAN RME is appropriate for wetting and precleaning all types of fibres. Due to its good wetting property, the product makes the exhaustion of fabric better in the washing machine. It is suitable for scouring processes as well as alkali washing and bleaching processes.

Recipe proposals

In the discontinuous range application amounts of

1.0 - 2.0 g/l FELOSAN RME

are normally sufficient, whereas in continuous processes the application amounts should be

5.0 - 10.0 g/l FELOSAN RME

Recipe example for discontinuous pretreatment processes

0.5 – 1.0 g/l	CONTAVAN GAL
1.0 - 2.0 g/l	FELOSAN RME
1.5 – 2.0 g/l	NaOH 100 %
1.5 – 3.0 g/l	H ₂ O ₂ 50 % for pretreatment of colour fabric
6.0 – 8.0 g/l	H ₂ O ₂ 50 % for full white
0.3 – 0.6 %	TUBOBLANC HA liq

Recipe examples for continuous pretreatment:

Cold bleach

6.0 – 10.0 g/l	CONTAVAN GAL
3.0 – 10.0 g/l	FELOSAN RME
10.0 – 30.0 g/l	NaOH 100 %
20.0 – 60.0 ml/l	H ₂ O ₂ 50 %
0.0 – 5.0 g/l	Sodium persulphate

Pad-steam-bleach

6.0 – 10.0 g/l	CONTAVAN GAL
3.0 – 10.0 g/l	FELOSAN RME
10.0 – 20.0 g/l	NaOH 100 %
20.0 – 40.0 ml/l	H ₂ O ₂ 50 %

We reserve the right to modify the product and technical leaflet.

Our department for applied technique is always at your service for further information and advice.

Our technical advice and recommendations given verbally, in writing or by trials are believed to be correct. They are neither binding with regard to possible rights of third parties nor do they exempt you from your task of examining the suitability of our products for the intended use. We cannot accept any responsibility for application and processing methods which are beyond our control.

Edition: May, 2024

CHT GERMANY GMBH, P.O. Box 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, homepage: www.cht.com

CHT TURKEY KİMYA SAN. VE TİC.A.Ş., Akçaburgaz Mah. 3118. Sok. No:2 Esenyurt/İstanbul, Tel: +90 212 886 79 13, Fax:+90 212 886 93 47,

Email: info.turkey@cht.com